



— 1876 —
THE PROFESSIONAL RANGE

TECHNICAL DATA SHEET

READY MIXED PLASTER SKIM & REPAIR

1876 THE PROFESSIONAL RANGE



DESCRIPTION

Bartoline 1876 Ready Mixed Plaster Skim & Repair is suitable for repairs on plaster and plasterboard prior to decorating. It has excellent wet adhesion making it easy to apply, will not slump on vertical surfaces and can be easily smoothed. It will cover holes up to 3mm deep but for larger cavities Bartoline Ready to Use All Purpose Filler should be used followed by Plaster Skim & Repair.

DIRECTIONS

Preparation: Surfaces should be sound, dry, clean and free from damp, dust and grease. Surfaces painted with gloss should be sanded to provide a key. Nail heads in plasterboard should be knocked below the surface level and covered with an oil-based paint to prevent rusting.

Application: Apply Bartoline 1876 Ready Mixed Plaster Skim & Repair to the surface using a large brush, trowel or other suitable spreader. After the initial setting the surface can be smoothed over using a wet trowel. Alternatively, the surface can be allowed to dry thoroughly and smoothed down using fine sandpaper. When the surface is dry, it can be painted or wallpapered over. Surfaces should be sealed with a plaster sealer or sealer/PVA mix before wallpapering.

CLEANING & STORAGE

After use, ensure lid is firmly replaced. Clean tools with water before plaster sets hard. PROTECT FROM FROST.

TECHNICAL DATA

Measurement	Value	Test Method
Physical State	Paste	Visual
Colour	White	Visual
Odour	PVA Type	N/A
VOC content	None	N/A
Viscosity	4000 - 4900	Lamy MSR4
pH	7.2 - 8.0	N/A
Specific Gravity	1.690 - 1.790	N/A

PACKING SPECIFICATION

Size	Product Code	Pack Barcode	Carton Barcode	Packs Per Carton	Cartons Per Pallet	Packs Per Pallet	Ti	Hi
2.5L	52832600	5010789832605	N/A	N/A	N/A	180	30	6
5L	52832573	5010789832452	N/A	N/A	N/A	75	25	3

HEALTH & SAFETY

See MSDS for full information.

CUSTOMS TARIFF CODE

3214 1090.

SHIPPING CLASSIFICATION

Non-Hazardous for shipping purposes.